



# TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453  
23825 15<sup>th</sup> Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815  
[DoctorTile@aol.com](mailto:DoctorTile@aol.com) [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com) (805) 444-8453

TIA's Client: 20201228 BS

**Aquabella USA, LLC**  
**Mr. Brian L. Streadbeck**  
**450 South Alpine Highway**  
**Alpine, Utah 84004**

Telephone: (833) 985-2955  
[info@aquabellatile.com](mailto:info@aquabellatile.com)

Tile: **Shimmer Series**

SH-1290 - ANTIGUA BLEND 1X2	SH-891 - BERMUDA BLOCK RANDOM	SH-1194 - AQUAMARINE BLEND 1X1
SH-1291 - BERMUDA BLEND 1X2	SH-894 - AQUAMARINE BLOCK RAND	SH-1195 - LIGHT BROWN 1X1
SH-1294 - AQUAMARINE BLEND 1X2	SH-895 - LT BROWN BLOCK RANDOM	SH-1196 - DARK BROWN BLEND 1X1
SH-1295 - LIGHT BROWN 1X2	SH-1190 - ANTIGUA BLEND 1X1	
SH-890 - ANTIGUA BLOCK RANDOM	SH-1191 - BERMUDA BLEND 1X1	

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random. Specification: ASTM C 648  
Source: Tiles submitted by Client to Laboratory and selected at random from unopened containers.

## Report of Test

### **BREAKING STRENGTH (ASTM C 648)**

Standard Test Method for Breaking Strength of Ceramic Tile. This method provides the means for establishing whether or not this tile meets the strength requirements, which may appear in tile specifications. Tile strength is the force in pounds-force (or Newton's), as read from the pressure gauge, necessary to cause the tile to break. The load was applied at the rate of 1000 lbf/min. The tile samples were placed on a test fixture having three (3) supports located in a circle three and fifteen-thirty-seconds (3 15/32) inches in diameter with the load applied at the center as per specifications.

Requirements: ANSI A 137.1 (General) Breaking Strength. When tested as described in ASTM C 648, the average breaking strength for glazed wall tile shall be 90 and for glazed paver tile 250 pounds or greater.

The tile types and categories listed above yielded test values greater than Industry's requirements.

Test Results: **Passed**

Sincerely,

Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021  
President/CEO of TILE INSTITUTE of AMERICA