

TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453
23825 15th Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815

DoctorTile@aol.com

DoctorTile1@gmail.com

[\(805\) 444-8453](tel:(805)444-8453)

TIA's Client: 20201228 BS

Aquabella USA, LLC
Mr. Brian L. Streadbeck
450 South Alpine Highway
Alpine, Utah 84004

Telephone: (833) 985-2955
info@aquabellatile.com

Tile: **Texas Series**

TEXAS - AMARILLO 6X6	TEXAS - AMARILLO 1X2	TEXAS - AMARILLO 6X6 SBN
TEXAS - FRISCO 6X6	TEXAS - FRISCO 1X2	TEXAS - FRISCO 6X6 SBN
TEXAS - LAREDO 6X6	TEXAS - LAREDO 1X2	TEXAS - LAREDO 6X6 SBN

Conditions: New tiles were sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

TEST CONDUCTED:

Resistance of Tile to Chemical Substances (ASTM C650)


Procedure: This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances (10% Hydrochloric Acid & 10% Potassium Hydroxide). The temperature was controlled at 75±5 ° F (24±3 ° C) with an exposure time of 24 hours.

Requirements: ANSI A 137.1 (General). When tested as described in ASTM C 650, the Tile shall Not be affected.

The tile types and categories listed above yielded test values compliant with Industry's requirements.

Test Results: **Passed**

Sincerely,



Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021
President/CEO of TILE INSTITUTE of AMERICA