



# TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453  
23825 15<sup>th</sup> Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815  
[DoctorTile@aol.com](mailto:DoctorTile@aol.com) [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com) (805) 444-8453

TIA's Client: 20201228 BS

**Aquabella USA, LLC**  
**Mr. Brian L. Streadbeck**  
**450 South Alpine Highway**  
**Alpine, Utah 84004**

Telephone: (833) 985-2955  
[info@aquabellatile.com](mailto:info@aquabellatile.com)

Tile: **Voyage Series**

|                      |                      |
|----------------------|----------------------|
| VG-840 - ANCHOR 1X2  | VG-946 - NARROWS 1X1 |
| VG-841 BEACON 1X2    | VG-948 - REEF 1X1    |
| VG-845 JETTY 1X2     | ANCHOR 2X4           |
| VG-846 - NARROWS 1X2 | NARROWS 2X4          |
| VG-848 - REEF 1X2    | REEF 2X4             |
| VG-940 - ANCHOR 1X1  |                      |

Conditions: New tiles sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

## Report of Test

### STAIN RESISTANCE (T-72)

Standard Test Method for Stain Resistance of Ceramic Tile. This method provides the means for establishing whether this tile can resist staining from six commonly used materials, which may appear in tile specifications. The tile samples were prepared as per specifications with the common household materials (each material having one sample covered with a Petri dish and the other uncovered) and left for 24 hours, and then cleaned with Ajax Industrial Cleaner and water.

### Observation of Surface Stain

| <u>Sample Tiles</u> | <u>Staining Materials</u> | <u>Uncovered</u> | <u>Covered</u> |
|---------------------|---------------------------|------------------|----------------|
| 1.                  | Coca Cola                 | No Stain         | No Stain       |
| 2.                  | Lemon Juice               | No Stain         | No Stain       |
| 3.                  | Mustard                   | No Stain         | No Stain       |
| 4.                  | Bacon Grease              | No Stain         | No Stain       |
| 5.                  | Catsup                    | No Stain         | No Stain       |
| 6.                  | Wesson Oil                | No Stain         | No Stain       |

**Requirements:** When tested as described. No evidence of any surface stain remaining, and all traces of the staining materials can be washed from the tile's surface.

Test Results: **Pass**

Sincerely,

A handwritten signature in cursive script that reads "Gerald M. Halweg". The signature is written in black ink and is positioned above the typed name and title.

Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021  
President/CEO of TILE INSTITUTE of AMERICA