

# TILE INSTITUTE of AMERICA

1262 Bouquet Circle, Thousand Oaks, California 91362 Telephone: (805) 371-TILE (8453) Facsimile: (805) 371-8453  
23825 15<sup>th</sup> Avenue SE #110, Bothell, Washington 98021 240 Makee Road, Suite PH-A, Honolulu, Hawaii 96815  
[DoctorTile@aol.com](mailto:DoctorTile@aol.com) [DoctorTile1@gmail.com](mailto:DoctorTile1@gmail.com) (805) 444-8453

TIA's Client: 20201228 BS

**Aquabella USA, LLC**  
**Mr. Brian L. Streadbeck**  
**450 South Alpine Highway**  
**Alpine, Utah 84004**

Telephone: (833) 985-2955  
[info@aquabellatile.com](mailto:info@aquabellatile.com)

Tile: **Tidal Wave Series**

TW-3390 - RIP CURL 3X3	TW-3394 - BREAKER 3X3
TW-3392 - SWELL 3X3	TW-3395 - CREST 3X3

Conditions: New tiles sent to TILE INSTITUTE of AMERICA in sealed manufacturer's boxes from client above and selected at random.

## Report of Test

### STAIN RESISTANCE (T-72)

Standard Test Method for Stain Resistance of Ceramic Tile. This method provides the means for establishing whether this tile can resist staining from six commonly used materials, which may appear in tile specifications. The tile samples were prepared as per specifications with the common household materials (each material having one sample covered with a Petri dish and the other uncovered) and left for 24 hours, and then cleaned with Ajax Industrial Cleaner and water.


### Observation of Surface Stain

Sample Tiles	Staining Materials	Uncovered	Covered
1.	Coca Cola	No Stain	No Stain
2.	Lemon Juice	No Stain	No Stain
3.	Mustard	No Stain	No Stain
4.	Bacon Grease	No Stain	No Stain
5.	Catsup	No Stain	No Stain
6.	Wesson Oil	No Stain	No Stain

**Requirements:** When tested as described. No evidence of any surface stain remaining, and all traces of the staining materials can be washed from the tile's surface.

Test Results: **Pass**

Sincerely,

  
Gerald M. Halweg, CTC, CSI, TTA. Date: July 1, 2021  
President/CEO of TILE INSTITUTE of AMERICA