



TILE INSTITUTE of AMERICA

23825 15th Avenue SE #149, Bothell, WA 98021 § 240 Makee Road, Penthouse-B, Honolulu, Hawaii 96815
(805) 444-(TILE) 8453 DoctorTile@aol.com or DoctorTile1@gmail.com

TIA's Client: 20260406 **FREEZE THAW**
May 16, 2026

Aquabella/Main Street Art, Inc.
Mr. Brett Streadbeck and Mr. Brian L. Streadbeck
11906 Brittmoore Park Dr.
Houston, Texas 77041

Telephone: (833) 985-2955
info@aquabellatile.com

Tile: **LIFESTYLE** Series (Item Description & Tile Color Name) Factory **A-26**. Nominal size: Porcelain Tile.

- **LIGHT GREY 2"x18"**
- **SEA WATER 2"x18"**
- **TURQUOISE 2"x18"**
- **WHITE 2"x18"**

Conditions: New tiles were sent to Tile Institute of America, from client above, and selected at random for testing.
Standard Test Method for RESISTANCE TO FREEZE THAW CYCLING ASTM C1026.

Ten Specimens were placed into the freezing chamber to 0°F (-18°C) within a period of 6-8 hours and placed into water that was at a temperature from 50°F to 60°F (10°C to 16°C) for ≥30 minutes.

Requirements: After 45 Cycles-

The tile units are to show no evidence of failure or damage to Tile Body or Surfaces.

Any damage to the specimen is reported with the abbreviation as follows:

Cz = crazing, Ch = Chipping, Sp = spalling, Bc = body checks, Cr = cracks.

Testing Results: All units described above have PASSED.

Sincerely,

Gerald M. Halweg, M.Ed., CTC, CSI, TTA
President/CEO of TILE INSTITUTE of AMERICA