



TILE INSTITUTE of AMERICA

23825 15th Avenue SE #149, Bothell, WA 98021 § 240 Makee Road, Penthouse-B, Honolulu, Hawaii 96815
(805) 444-(TILE) 8453 DoctorTile@aol.com or DoctorTile1@gmail.com

TIA's Client: 20260406 Chemical Resistance
April 24, 2026

AquaBella/Main Street Art, Inc.
Mr. Brett Streadbeck and Mr. Brian L. Streadbeck
11906 Brittmoore Park Dr.
Houston, Texas 77041

Telephone: (833) 985-2955
info@aquabellatile.com

Tile: OLYMPUS Series (Item Description & Tile Color Name) Factory A-28. Nominal size: Porcelain Mosaics.

- ADONIS 1"x2"
- ADONIS 3"x6"
- APOLLO 1"x2"
- APOLLO 3"x6"
- ARES 1"x2"
- ARES 3"x6"
- ATHENA 1"x2"
- ATHENA 3"x6"
- POSEIDON 1"x2"
- POSEIDON 3"x6"
- TRITON 1"x2"
- TRITON 3"x6"

Conditions: New tiles were sent to Tile Institute of America, from client above, and selected at random.

TEST CONDUCTED: Resistance of Tile to Chemical Substances (ASTM C650)

Procedure: This test method covers a procedure for determining whether, and to what degree, tiles are affected by prolonged exposure to chemical substances (10% Hydrochloric Acid & 10% Potassium Hydroxide). The temperature was controlled at 75±5 ° F (24±3 ° C) with an exposure time of 24 hours.

Requirements: ANSI A 137.1 (General). When tested as described in ASTM C 650, the Tile shall **not** be affected.

The tile types and categories listed above yielded test values compliant with Industry's requirements.

Testing Results: All Passed

Sincerely,

Gerald M. Halweg, M.Ed., CTC, CSI, TTA,
President/CEO of TILE INSTITUTE of AMERICA