



TILE INSTITUTE of AMERICA

23825 15th Avenue SE #149, Bothell, WA 98021 § 240 Makee Road, Penthouse-B, Honolulu, Hawaii 96815
(805) 444-(TILE) 8453 DoctorTile@aol.com or DoctorTile1@gmail.com

TIA's Client: 20260406 Stain Resistances
April 18, 2026

Aquabella/Main Street Art, Inc.
Mr. Brett Streadbeck and Mr. Brian L. Streadbeck
11906 Brittmoore Park Dr.
Houston, Texas 77041

Telephone: (833) 985-2955
info@aquabellatile.com

Tile: OLYMPUS Series (Item Description & Tile Color Name) Factory A-28. Nominal size: Porcelain Mosaics.

- ADONIS 1"x2"
- ADONIS 3"x6"
- APOLLO 1"x2"
- APOLLO 3"x6"
- ARES 1"x2"
- ARES 3"x6"
- ATHENA 1"x2"
- ATHENA 3"x6"
- POSEIDON 1"x2"
- POSEIDON 3"x6"
- TRITON 1"x2"
- TRITON 3"x6"

STAIN RESISTANCE (T-72)

Standard Test Method for Stain Resistance of Tile. This method provides the means for establishing whether this tile can resist staining from six commonly used materials, which may appear in tile specifications. The tile samples were prepared as per specifications with the common household materials (each material having one sample covered with a Petri dish and the other uncovered) and left for 24 hours and then cleaned with Ajax Industrial Cleaner and water.

Observation of Surface Stain

<u>Sample Tiles</u>	<u>Staining Materials</u>	<u>Uncovered</u>	<u>Covered</u>
1.	Coca Cola	No Stain	No Stain
2.	Lemon Juice	No Stain	No Stain
3.	Mustard	No Stain	No Stain
4.	Bacon Grease	No Stain	No Stain
5.	Catsup	No Stain	No Stain
6.	Wesson Oil	No Stain	No Stain

Requirements: When evaluated as described. No evidence of any surface stain remaining, and all traces of the staining materials can be washed from the tile's surface.

Testing Results: All Passed

Sincerely, 

Gerald M. Halweg, M.Ed., CTC, CSI, TTA.
President/CEO of TILE INSTITUTE of AMERICA